



## PAINTER'S SELECT Interior/Exterior Gloss Polyurethane Floor

### DESCRIPTION

An extremely durable oil based porch and floor coating resists abrasion, scuffing, chipping and cracking.

#### DP FORMULA ANALYSIS

Resin Type-Alkyd/Polyurethane

Sheen/Type Finish

6 + at 60°/Gloss

Weight per Gallon = 9.42

Percent Solids by Weight = 67.0 %

Percent Solids by Volume =52.0 %

Viscosity = 77-82 KU

V.O.C. = Less than 375 g/L

Coverage=400-450 sq. ft. per gallon

#### Product Features

- Easy-to-clean, high-gloss finish
- Highly durable formula will not dull or fade

#### Colors/Bases

##### Available:

- DP-1 White
- DP-2 Black
- DP-3 Light Gray
- DP-4 Tile Red
- DP-5 Medium Gray
- DP-10 Dark Gray
- DP-13 Rich Brown
- DP-15 Hunter Green
- DP-T Tint Base
- DP-D Deep Base
- DP-N Neutral Base

#### RECOMMENDED USE

Covered exterior wood, interior wood, and interior concrete. Use on porches, basement floors, utility rooms and other surfaces on which a wear-resistant coating is needed.

**THINNING:** DO NOT THIN

**DRY TIME:** Dries overnight. Low temperature or high humidity may increase dry time. On garage floors allow paint to dry 48 hours before driving on paint. Shield areas under tires for first 2 weeks with corrugated cardboard.

**COVERAGE:** 450 sq. ft. per gallon .

**CLEAN UP:** Use mineral spirits (paint thinner) to clean up.

Properly dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only) or go to [www. Earth911.org](http://www.Earth911.org).

**STORAGE:** Do not expose this container to excessive heat. Close container after each use. Keep from freezing.

#### APPLICATION METHODS

Stir or mix paint before using and intermix all containers for color uniformity.

The dried film will become slippery when wet. The addition of a non-slip agent such as silica sand is recommended prior to application.

Apply as-is with brush, roller or pad painter. For spraying information contact your paint specialist. Do not overspread.

Surface temperature must be above 40°F (5°C).

#### SURFACE PREP

- Remove dirt, dust, grease and oil residue, loose and peeling paint or rust.
- Glossy areas must be dulled by sanding.
- Spot coat worn or bare areas.
- Allow new concrete to age 90 days before painting.
- Acid etch all bare concrete to the roughness of 100 grit sandpaper (this may require several etchings) before painting.