



## PAINTER'S SELECT Basics Interior/Exterior Floor & Utility Enamel

### DESCRIPTION

A quality economical all purpose floor & utility enamel.

### VE FORMULA ANALYSIS

Resin Type- Alkyd/Polysaccharide

Sheen/Type Finish:

60+ at 60°/Gloss

Weight per Gallon = 9.58

Percent Solids by Weight = 57.0

Percent Solids by Volume = 40.0

Viscosity = 78-84 KU

V.O.C. = Less than 375 g/L

Coverage=350-450 sq. ft. per gallon.

### Product Features

- Ideal for use on floors, railings & utility areas
- Abrasion resistant
- Easy to clean high-gloss finish

### Colors/Bases

#### Available:

- VE-1 Light Gray
- VE-2 Battleship Gray
- VE-3 Brown
- VE-4 Tile Red
- VE-5 Green
- VE-9 White
- VE-14 Black

### RECOMMENDED USE

Covered exterior wood, interior wood, and interior concrete. Use on porches, basement floors, utility rooms and other surfaces on which a wear-resistant coating is needed.

**THINNING:** DO NOT THIN

**DRY TIME:** Dries overnight. Low temperature or high humidity may increase dry time. On garage floors allow paint to dry 48 hours before driving on paint. Shield areas under tires for first 2 weeks with corrugated cardboard.

**COVERAGE:** 450 sq. ft. per gallon.

**CLEAN UP:** Use mineral spirits (paint thinner) to clean up.

Properly dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only) or go to [www.Earth911.org](http://www.Earth911.org).

**STORAGE:** Do not expose this container to excessive heat. Close container after each use. Keep from freezing.

### APPLICATION METHODS

Stir or mix paint before using and intermix all containers for color uniformity.

The dried film will become slippery when wet. The addition of a non-slip agent such as silica sand is recommended prior to application.

Apply as-is with brush, roller or pad painter. For spraying information contact your paint specialist. Do not overspread.

Surface temperature must be above 40°F (5°C).

### SURFACE PREP

- Remove dirt, dust, grease and oil residue, loose and peeling paint or rust.
- Glossy areas must be dulled by sanding.
- Spot coat worn or bare areas.
- Allow new concrete to age 90 days before painting. Acid etch all bare concrete to the roughness of 100 grit sandpaper (this may require several etchings) before painting.