



## Tru-Seal Clear Multi-Surface Waterproofing Sealer – CS-1

### DESCRIPTION:

Penetrates and protects wood, masonry and concrete

### CS-1 FORMULA ANALYSIS

Sheen/Type Finish Clear

Weight per Gallon 6.68 pounds

Percent Solids by Weight 25.13%

Percent Solids by Volume 21.83%

Viscosity 6"-12" Ford Cup

V.O.C. Less than 600 g/L

### Product Features

Formulated to protect against moisture damage to:  
Brick, Patios, Hardboard, Wood,  
Masonry, Concrete and other porous surfaces

### CS-1 Clear

**RECOMMENDED USE:** Protects wood, concrete, masonry, brick, composition surfaces, and other porous surfaces.

**DRY TIME:** 24-48 hours for a single coat. If a second coat is needed, allow 48 hours before application.

**CLEAN UP:** Clean up tools, drips and spills immediately with mineral spirits (paint thinner).

**DISPOSAL:** Properly Dispose of all soiled rags. To recycle or properly dispose of paint in your community, call 1-800-CLEANUP (USA only) or visit [www.Earth911.org](http://www.Earth911.org).

**LIMITATIONS:** Do not apply paint, stain or varnish over Tru-Seal, or use as an additive to any coating. Do not apply over rubber, plastic, asphalt, canvas or sealed surfaces.

### APPLICATION METHODS:

Apply by brush, roller, dip or spray without thinning. A garden sprayer is suitable for spraying. Apply liberally in a uniform manner. If too much is applied, a non-drying residue will form. This may be removed by wiping with a rag. Test for compatibility prior to application. Average coverage is 100 to 200 sq. ft (9 to 19 square meters) per gallon (3.78L) depending on surface porosity.

**DO NOT APPLY OVER PAINT, RECENTLY STAINED SURFACES, VARNISH, RUBBER, PLASTIC, ASPHALT OR SEALED SURFACES. DO NOT USE AS AN ADDITIVE. DO NOT BLEND OR MIX WITH OTHER TRU-SEAL WATER-PROOFING PRODUCTS.**

### SURFACE PREP:

All surfaces must be clean, dry and porous. Surface is suitable for application if a small amount of water can be quickly absorbed.