



## Exterior 100% Acrylic Solid Color Deck, Siding & Fence Stain - ADS

### DESCRIPTION

100% Acrylic Solid Color Deck, Siding & Fence Stain for natural or pressure treated wood decks, siding & fences. Helps wood stand up to the harshest weather elements.

### ADS FORMULA ANALYSIS

Resin Type – Acrylic Latex

Sheen/Type Finish:

3-8 @60° / Penetrating Stain

Weight per Gallon = 10.92 lbs.

Percent Solids by Weight = 53.44

Percent Solids by volume = 39.88

Viscosity Range = 80-85 KU

V.O.C. = Less than 100 g/L

### Product Features

- Ideal for natural or pressure-treated wood decks
- Acrylic latex formula resists scuffing, color fade & peeling
- Tough water repellent coating
- Cleans up with soap & water

### COLORS AND TINTING

ADS-1 White

ADS-27 Rustic Brown

ADS-7 Cedar

ADS-10 Redwood

ADS-LT Light Base

ADS-N Neutral Base

**RECOMMENDED USE:** Exterior above ground natural or pressure-treated wood structures such as decks, fences, steps, walkways, lattice, T1-11 as well as stucco, masonry and cement patios.

**THINNING:** DO NOT THIN

**DRY TIME: 77°F @50% humidity:** Dry to the touch within 2 to 4 hours. Recoat usually within 24 hours. High humidity or low temperatures may increase dry time. Fully tintable.

**COVERAGE:** 250-350 sq. ft. per gallon first coat, 350-450 sq. ft. per gallon second coat, depending on the porosity of the wood.

**CLEAN UP & DISPOSAL:** Wash tools with warm water and soap immediately after application.

Call 1-800-CLEANUP (USA only) or visit [www.Earth911.org](http://www.Earth911.org). Properly dispose of used rags. Protect unused portion from freezing

**STORAGE:** Do not expose this container to excessive heat. Close container after each use. Keep from freezing.

### APPLICATION:

- Apply only to properly prepared and cleaned wood surfaces.
- On redwood, cedar, rough fir or pine siding an exterior oil primer must be applied to prevent bleeding into the topcoat.
- On non-porous surfaces apply only one coat, as two coats may result in a high sheen finish.
- On very porous or severely weathered wood two coats may necessary.
- Do not apply if rain or dew is expected within 48 hrs or if outside temperature could drop below 50°F
- Do not apply in hot sun.
- Stir thoroughly before and during use. Intermix all containers for uniform color.
- Use a premium brush or pad applicator. A pump-up sprayer or roller can be used to apply the stain but back brushing with a brush is necessary to get the stain into the wood.
- DO NOT OVER APPLY.
- Spread well, do not puddle or accumulate on wood surface.
- Moving left to right, apply to two or three boards at a time leaving a “wet edge” to prevent lapping.
- Saturate end grain.